

UN-F17T18X10X10

ROHS

铁氧体锰锌磁环(Ferrite Mn-Zn Magnetic Ring)

电气要求/Electrical Requirement

◆ 电感/Inductance:

$L \geq 5.0\mu\text{H}$ at 1kHz/0.25V

测试要求/Test Requirements

◆ 测试环境/Test environment:

温度/Temperature: $25 \pm 3^\circ\text{C}$

湿度/Humidity: $60 \pm 20\%$

◆ 测试条件/Test Conditions:

导线/Wire: $\Phi 0.5\text{mm}$ 漆包线/Enameled wire


匝数/Number of turns: 0.5圈/Laps



www.unsemi.com.tw



尺寸 (单位: 毫米) /Dimension(unit:mm)



符号/Symbol	毫米/Millimeters
A	18.0 ± 0.6
B	10.0 ± 0.5
C	10.0 ± 0.5

克重/Weight: 8.0g(REF.)

外观/Appearance

项目/Item	标准值/Standard value
一处缺陷面积/Area of a breakage	$\leq 1.0\text{mm}^2$
总缺陷面积/ALL area of the breakage	$\leq 2.0\text{mm}^2$
缺陷深度/The depth of the breakage	$\leq 0.4\text{mm}$
毛刺长度/The length of burr	$\leq 0.2\text{mm}$


材质特性/Material Characteristics

初始磁导率 Initial permeability	比损耗因子 Relative loss factor	比温度系数 Relative temperature coefficient	饱和磁通密度 Saturation magnetic flux density	剩磁 Remanence	矫顽力 Coercivity	居里温度 Curie temperature	电阻率 Electrical resistivity	使用范围 Applied frequency range	密度 Density
μ_i	$\text{Tan}\delta/\mu_i$	$\alpha\mu_i\gamma$	Bs	Br	HC	Tc	ρ	F	d
$\pm 20\%$	$\times 10^{-6}$	$\times 10^{-6}$	(MT)	(MT)	(A/m)	($^{\circ}\text{C}$)	($\Omega\cdot\text{m}$)	(Mhz)	(g/cm^3)
7000	<30 (0.1MHz)	-0.5~2.0	420 (1194A/m)	110	7.0	>125	0.2	<0.1	4.9

实测数据/Measured Data

编号 No.	电感值(μH) Inductance	尺寸(mm) Dimension		
	L	A	B	C
1	6.82	18.06	9.95	10.02
2	6.81	18.02	9.96	10.01
3	6.84	18.11	9.94	10.05
4	6.83	18.08	9.98	9.99
5	6.81	18.04	9.92	10.00
6	6.84	18.11	9.90	10.05
7	6.80	18.01	9.98	10.05
8	6.79	17.97	9.98	9.97
9	6.84	18.11	9.92	10.00
10	6.83	18.10	9.93	10.05

特性曲线 (仅供参考) / Characteristic Curve (for reference only)



Disclaimer

UNSEMI RESERVES THE RIGHT TO MAKE CHANGE ON OUR PRODUCTS , PRODUCTS SPECIFICATION AND DATA WITHOUT NOTICE TO IMPROVE RELIABILITY, FUNCTION OR DESIGN OR OTHERWISE.

UN SEMICONDUCTOR LIMITED its affiliates, agents, and employees, and all persons acting on its or their behalf (collectively, "UNSEMI") does not give any representations or warranties for any errors, inaccuracies or incompleteness contained in any datasheet or in any other disclosure relating to any product.

In no event shall UNSEMI be liable for any indirect, incidental, punitive, special or consequential damages (including any and all implied warranties, warranties of fitness for particular purpose, non-infringement and merchantability.) whether or not such damages are based on tort (including negligence), warranty, breach of contract or any other legal theory.

Statements regarding the suitability of products for certain types of applications are based on UNSEMI knowledge of typical requirements that are often placed on UNSEMI products in generic applications. Such statements are not binding, statements about the suitability of products for a particular application. It is the customer's responsibility to validate that a particular product with the properties described in the product specification is suitable for use in a particular application. Parameters provided in datasheets or specifications may vary in different applications and performance may vary over time. All operating parameters, including typical parameters, must be validated for each customer application by the customer's technical experts. Product specifications do not expand or otherwise modify UNSEMI's terms and conditions of purchase, including but not limited to the warranty expressed therein.

Unless otherwise agreed in writing, UNSEMI product is not designed, authorized or warranted to be suitable for use in medical life-saving, or life-sustaining application , nor in applications where failure or malfunction of a UNSEMI product can reasonably be expected to result in personal injury, death or severe property or environmental damage. UNSEMI and its suppliers accept no liability for inclusion or use of UNSEMI products in such equipment or applications and therefore such inclusion and/or use is at the customer's own risk.

All referenced brands, product names, service names and trademarks are the property of their respective owners.