

功率型热敏电阻
POWER NTC THERMISTOR

特点 Characteristic

- ◆ 抑制浪涌电流能力强
Strong Surge Suppression Capability
- ◆ 反应速度快
Fast Respose
- ◆ 材料系数(B值)大，残余电阻小
Big material constant (B value),small residual resistance
- ◆ 寿命长，可靠性高
Long life and high reliability
- ◆ 产品系列全，工作范围宽
Complete series,wide applications
- ◆ 新型陶瓷材料和均匀化工艺效率高，性能好
New Ceramic Material and Homogenization Process for
Volume-efficient & High- performance Design

应用领域 Application

- ◆ 转换电源，开关电源，UPS电源
Switching power-supply, switch power, UPS power
- ◆ 镇流器及各类加热器
Electronic energy saving lamps,electronic ballast and all kinds of
electric heater
- ◆ 各类显像管、显示器
All kinds of RT display
- ◆ LED驱动电路
LED driver circuit
- ◆ 变压器、逆变器
Transformers and Inverters
- ◆ 软启动电机
Soft-start motors


命名规则 Naming Convention

NTC XX D - 13 M
(1) (2) (3) (4) (5)


- (1) NTC : 中性标志 Nevtral Sign
- (2) 额定功率阻值 Rated Power Resistance
- (3) 产品形状 Shape: D : 圆片形 Disk
- (4) 产品直径 Dimension : 13 : 13mm
- (5) 零功率电阻公差 Zero power resistance tolerance : M : 20%



www.unsemi.com.tw



结构图 Structure



主要技术参数 Main Technical Parameters


型号 Part No.	R25 (Ω)	最大稳态电流 Max. steady State current (A)	残余电阻* Residual Resistance (Ω)	耗散系数* Dissipation Factor (mw/°C)	热时间常数* Thermal time Constant (s)	最大允许使用容量值 Max. allowable capacity value 240V/120V (μF)	B值 (K)	工作温度 Operating Temperature (°C)
1.5D-13	1.5	7.0	0.093	≥13	≤70	220/270	2700	-40~+175
2.5D-13	2.5	6.0	0.112	≥13	≤70	220/270	2700	-40~+175
3D-13	3.0	6.0	0.156	≥13	≤70	220/270	2700	-40~+175
5D-13	5.0	5.0	0.161	≥13	≤70	220/560	2800	-40~+175
8D-13	8.0	4.0	0.286	≥13	≤70	330/1200	3000	-40~+175
10D-13	10	4.0	0.286	≥13	≤70	330/1200	3000	-40~+175
12D-13	12	3.0	0.495	≥13	≤70	330/1200	3000	-40~+175
15D-13	15	3.0	0.498	≥13	≤70	330/1200	3100	-40~+175
16D-13	16	3.0	0.463	≥13	≤70	330/1200	3100	-40~+175
20D-13	20	3.0	0.574	≥13	≤70	330/1200	3200	-40~+175
22D-13	22	3.0	0.592	≥13	≤70	330/1200	3200	-40~+175
25D-13	25	2.0	0.632	≥13	≤70	330/1200	3200	-40~+175
30D-13	30	2.0	0.701	≥13	≤70	330/1200	3200	-40~+175
33D-13	33	2.0	0.772	≥13	≤70	330/1200	3200	-40~+175
47D-13	47	2.0	1.103	≥13	≤70	220/820	3200	-40~+175
50D-13	50	2.0	1.172	≥13	≤70	220/820	3200	-40~+175
60D-13	60	2.0	1.405	≥13	≤70	220/820	3200	-40~+175

说明:*表示参考值。


Note:*Represents a reference value.

阻温特性和静态伏安特性 R-T Characteristic and Static Characteristic


电阻-温度曲线 Resistance-Temperature Curve



电压-电流曲线 Voltage-Current Curve




抑制浪涌电流示意图 Suppression of Inrush Current Diagram




特性 Characteristics

电阻-温度特性 Resistance-Temperature Characteristics	电压-电流特性 Voltage-Current Characteristics	温度-时间特性 Test Temperature-Time Characteristics
当功率型热敏电阻之环境温度或它本身的温度上升时，电阻值随之减小。 When the ambient temperature of the power type themistor is applied,or its temperature rises, the resistance decreases.	当功率型热敏电阻在小电流下工作时，由于功率太低，其电阻值保持固定而表现线性(符合欧姆定律$V/R=I$)。如果电流增加，功率型热敏电阻就会产生焦耳效应($P=V*I$)而使自己发热，其电阻随即减小表现(电流增加，电压下降)的状态。 When the power themistor works at small current when the power is too low,the resistance is kept constant and behave lineary (in acordance with Ohm's law,$V/R=I$).If the current increases,the power type themistor will produces a Joule effect ($P=V*I$) and makes itself hot.The resisance then deereases (current increases,voltage decreases) State.	功率型热敏电阻与环境达成热平衡所需的时间，主要决定于材料热容量(H)及散热系数(δ)。 The power type themistor achieves heat with the environment.The time required for the equilibrium is mainly determined by the heat of the metarial.Capacity(H) and heat transfer coefciant(delta).

最大电流降额曲线 Maximum Current Derating Curve



波峰焊参数 Wave Soldering Parameters



波峰焊参数仅供参考。热敏电阻器实际使用时，需要进行一些相关的验证。
The wave soldering parameters are for reference only. When thermistor is for practice use, some related validation is recommended.

推荐手工焊接参数 Recommended Hand-Solder Parameters

项目 Items	条件 Condition
烙铁头部温度 Temp. of Solder Head	360°C (max.)
焊接时间 Soldering Time	3 sec (max.)
焊接位置与涂装层距离 Distance from Thermistor	2mm (min.)

手工焊接，请注意焊接温度和焊接时间。
For hand soldering, please notice the solder tip temperature and the soldering time.

机械性能 Mechanical Performance

指标项目 Item	技术要求 Specification	测试条件/方法 Test Conditions & Methods
可焊性 Solder-ability	浸润部分上锡均匀， 上锡面积≥95% The terminals shall be uniformly tinned, and its area≥95%	将引出端沾助焊剂后，浸入到温度为240-245℃、 深度为15mm 的锡槽中锡面距 NTC 本体下端6mm 处，持续2-3秒。（参见 IEC68-2-20 /GB2423.28 试验Ta） Dipping the NTC terminals to a depth of 15mm in a soldering bath of 240-245℃ and to the place of 6mm far from NTC body for 2-3s (See IEC68-2-20 / GB2423.28 Ta)
耐焊接热 Resistance To Soldering Heat	无可见损伤 No visible mechanical damage. $\Delta R/RN \leq 20\%$ ($\Delta R = RN - RN' $)	根据 IEC68-2-20 (GB2423 .28) 试验Tb进行试验。 采用焊槽法，将引出端沾助焊剂后，浸入到温度为 265±5℃、深度为15mm的锡槽中，锡面距NTC本体 下端6mm处，维持10±1秒。在25±2℃条件下恢复 4~5h后，复测额定零功率电阻RN'。 Dipping the NTC terminals to a depth of 15mm in a soldering bath of 265±5℃ and to the place for 6mm below from NTC body for 10±1s. After recovering 4~5h under 25±2℃. The rated zero power resistance value RN' shall be measured. (See IEC68-2-20 /GB2423.28 Tb)
引出端强度 Strength of lead terminal	无可见损伤 No visible mechanical damage. $\Delta R/RN \leq 20\%$ ($\Delta R = RN - RN' $)	根据 IEC68-2-21 (GB2423 .29) 试验U进行试验。 试验 Ua: 拉力 0N，持续10S； 试验 Ub: 弯曲90°，拉力5N，持续10S； 扭转180°，拉力5N，持续10S。 在 25±2℃条件下恢复4~5h后，复测额定零功率电 阻 RN' Fasten the body and apply a force gradually to each lead until 10N and then keep for 10sec, Hold body and apply a force to each lead until 90° slowly at 5N in the direction of lead axis and then keep for 10sec, and do this in the opposite direction repeat for other terminal. After recovering 4~5h under 25±2℃, the rated zero power resistance value RN' shall be measured. (See IEC68-2-21/GB2423.29 Ua / Ub)

电气性能 Electrical Performance

指标项目 Item	技术要求 Specification	测试条件/方法 Test Conditions & Methods
额定零功率电阻 Rated Zero-Power Resistance RN (Ω)	$3 \pm 20\%$	环境温度 TA: $25^{\circ}\text{C} \pm 1^{\circ}\text{C}$ 测试电压: 1.5VDC 在常温TA条件下, 放置1~2小时 后测得阻值RN。 Ambient temp. Range: $25^{\circ}\text{C} \pm 1^{\circ}\text{C}$ (TA). Testing voltage: 1.5VDC After placing for 1~2 hours under TA, the resistance value shall be measured.
热耗散系数 δ (MW/ $^{\circ}\text{C}$) Thermal Dissipation Constant	≥ 9	在特定的环境温度下, 热耗散系数(δ)为热敏电阻电功率消耗(ΔP)与本体温度变化量 (ΔT)的比值。 The thermal dissipation constant(δ) could be calculated by the ratio of a change in power dissipation(ΔP) of the thermistor to a change in temperature(ΔT) of the thermistor at a specified ambient temperature
热时间常数 τ (S) Thermal Time Constant	≤ 30	热时间常数(τ)为在零功率条件下, 热敏电阻的温度下降到其最初温度与最终温度之差为63.2%时所需要的时间。 The time(τ) shall be measured within which the temperature change of NTC thermistor is reached at 63.2% of the ambient temperature change under zero power condition.
材料常数 Material Constant B	$2700 \pm 10\%$ $B = T_1 T_2 / (T_2 - T_1) \times \ln(R_1 / R_2)$	R1, R2 分别为 T1, T2温度下的零功率电阻 R1, R2 is zero-power resistance at T1, T2 $T_1 = 298.15 \text{ K}(25^{\circ}\text{C})$ $T_2 = 323.15 \text{ K}(50^{\circ}\text{C})$
最大稳态电流 (A)	无可见损伤 visible mechanical damage. $\Delta R_N / R_N \leq 20\%$ ($\Delta R = R_N - R_N' $)	环境温度: $25^{\circ}\text{C} \pm 2^{\circ}\text{C}$ 测试电流: 3.0A Ambient temp. Range: $25^{\circ}\text{C} \pm 2^{\circ}\text{C}$ Testing Current: 3.0A

可靠性试验 Reliability Test


指标项目 Item	技术要求 Specification	测试条件/方法 Test Conditions & Methods
温度循环测试 Temp. Cycling Testing	无可见损伤 No visible mechanical damage. $\Delta RN / RN \leq 20\%$ ($\Delta R = RN - RN'$)	在 $T_a = -40 \pm 3^\circ\text{C}$ 和 $T_b = 200 \pm 3^\circ\text{C}$ 的环境温度中各存放30分钟, 循环5次. 每次高低温循环都有在 $25 \pm 2^\circ\text{C}$ 的环境中过渡5分钟. 样品进行温度循环测试后, 取出放置室温 ($25 \pm 2^\circ\text{C}$), 4~5小时后测量零功率电阻 RN'. $T_a: -40 \pm 3^\circ\text{C} / 30\text{min} \rightarrow 25 \pm 2^\circ\text{C} / 5\text{min} \rightarrow T_b: 200 \pm 3^\circ\text{C} / 30\text{min} \rightarrow 25 \pm 2^\circ\text{C} / 5\text{min}$ Cycles: 5times After recovering 4~5h under $25 \pm 2^\circ\text{C}$, the rated zero power resistance value RN' shall be measured.
电循环测试 Electrical Cycling Testing	无可见损伤 No visible mechanical damage. $\Delta RN / RN \leq 20\%$ ($\Delta R = RN - RN'$)	环境温度: $25^\circ\text{C} \pm 2^\circ\text{C}$ 循环次数: 1,000次 通/断: 1分钟 / 5分钟 测试电流: 3.0A 样品置于室温 ($25 \pm 2^\circ\text{C}$) 4~5小时后, 测量其零功率电阻 RN' Ambient temp. Range: $25^\circ\text{C} \pm 2^\circ\text{C}$. Cycles: 1,000times On / Off: 1m / 5m Test Current 3.0A After recovering 4~5h under $25 \pm 2^\circ\text{C}$, the rated zero power resistance value RN' shall be measured.
持久性测试 LoadLife (Endurance) Testing	无可见损伤 No visible mechanical damage. $\Delta RN / RN \leq 20\%$ ($\Delta R = RN - RN'$)	环境温度: $25^\circ\text{C} \pm 2^\circ\text{C}$ 样品通过最大工作电流 3.0A, 1,000±24 小时后, 取出置于室温 ($25 \pm 2^\circ\text{C}$) 4~5小时后, 测量其零功率电阻 RN' Ambient temp. Range: $25^\circ\text{C} \pm 2^\circ\text{C}$; 3.0A/ 1,000±24h After recovering 4~5h under $25 \pm 2^\circ\text{C}$, the rated zero power resistance value RN' shall be measured.
耐湿性测试 Humidity Testing	无可见损伤 No visible mechanical damage. $\Delta RN / RN \leq 20\%$ ($\Delta R = RN - RN'$)	在温度 $40 \pm 2^\circ\text{C}$, 相对湿度 $93 \pm 3\%$ 的环境中放置 1000±24小时后, 取出置于室温 ($25 \pm 2^\circ\text{C}$) 4~5小时后, 测量其零功率电阻 RN' Ambient temp. range : $40^\circ\text{C} \pm 2^\circ\text{C}$ R.H.: $93 \pm 3\%$, Energized time: 1000±24h After recovering 4~5h under $25 \pm 2^\circ\text{C}$, the rated zero power resistance value RN' shall be measured.

术语 Glossary

项目 Item	描述 Description
R_{25}	标称零功率电阻值 Nominal Zero-power Resistance 25°C标准参考温度下零功率电阻的标称值，除非另有规定。 Nominal value of zero-power resistance at the standard reference temperature of 25°C, unless otherwise specified.
I_{max25}	25°C环境温度下的最大电流 Maximum Current at Ambient Temperature of 25°C 在25°C的环境温度下，可连续施加到热敏电阻器上的电流(直流或交流正弦波的有效值)最大值。 Maximum value of current (d.c. or r.m.s. values for Sine wave shaped a.c.) which can be continuously applied to the thermistor at an ambient temperature of 25°C.
B	B值 B value 用以下公式表示热灵敏指数 $B = \frac{T_a \times T_b}{T_b - T_a} \times \ln \frac{R_a}{R_b}$ R_a在温度T_a (单位为K)下测定的零功率电阻值(单位为Ω) R_b在温度T_b (单位为K)下测定的零功率电阻值(单位为Ω) $T_a = 298.15K$, $T_b = 358.15K$ Index of thermal sensitivity expressed by the formula $B = \frac{T_a \times T_b}{T_b - T_a} \times \ln \frac{R_a}{R_b}$ R_a is the zero-power resistance (Ω) at temperature T_a (K) R_b is the zero-power resistance (Ω) at temperature T_b (K) $T_a = 298.15K$, $T_b = 358.15K$
δ	耗散系数 Dissipation Factor 使热敏电阻器的温度升高1K所需消耗的功率，通常为规定的环境温度下功耗变化与热敏电阻器阻体温度变化之比。 Power dissipation required for a thermistor to raise its temperature by 1K and which is generally the ratio of the power dissipation change to the resulting thermistor body temperature change at a specified ambient temperature.
T_a	环境温度变化的热时间常数 Thermal Time Constant by Ambient Temperature Change 热敏电阻器对规定介质中环境温度63.2%的外部阶跃变化作出响应所需的时间。 Time required for a thermistor to respond to 63.2% of an external step change in ambient temperature in a defined medium.
$R_{min@I_{max25}}$	残余电阻 Residual Resistance 当热敏电阻器上流过最大电流并达到热平衡时的直流电阻值。 Inrush Current-limiting Thermistors value of the d.c. resistance of a thermistor when its thermal stability is reached with the maximum current passing.
C_{max}	最大允许电容量 Maximum Permissible Capacitance 在负载状态下，与一个热敏电阻器连接的电容器的最大允许电容量值。 Maximum permissible capacitance value of a capacitor which can be connected to a thermistor under loading.
P_{max}	最大功耗 Maximum Power Dissipation 在环境温度25°C下，可以连续施加在热敏电阻器上的最大功耗值。 Maximum value of the power dissipation which can be continuously applied to the thermistor at 25°C.

产品尺寸 Product Size

单位 Unit:mm



型号 Part No.	最大直径 Maximum Diameter Dmax	最大厚度 Maximum Thickness Tmax	引线直径 Lead Diameter d(±0.05)	引线间距 Lead Spacing F(±1.0)	Amax	L	
						直引线 Straight Lead	其他线型 Other Lines
XXD-13 Series	15.0	6.0	0.75	7.5	20.0	3.0~23	3.0~20

包装信息 Packaging Information

单位 Unit:Pcs


型号 Part No.	袋 Bag	盒 Box	箱 Carton
XXD-13 Series	500	5,000	10,000

型号 Part No.	编带 Braid	盒 Box	箱 Carton
XXD-13 Series	1,000	1,000	10,000

说明：默认袋装出货方式。
Note:The default bag shipping method.

编带尺寸 Braid Size

单位 Unit:mm



尺寸 Dimensions	毫米 Millimeters	尺寸 Dimensions	毫米 Millimeters
P0	12.7 ± 0.3	W2	3.0 max
P	12.7	t	0.5 ± 0.05
F	7.5 ± 0.5	D	15.0 max
P1	2.6 ± 0.8	D0	4.0 ± 0.3
P2	6.35 ± 1.3	d	0.75 ± 0.05
H	16.0 ± 1.0	A	0.5 max
W	18.0 ± 1.0	T	6.0 max
W0	8.0 / 10.0	ΔP	0 ± 0.2
W1	9.0 ± 1.0	Δh	2.0 max

Disclaimer

UNSEMI RESERVES THE RIGHT TO MAKE CHANGE ON OUR PRODUTS , PRODUCTS SPECIFICATION AND DATA WITHOUT NOTICE TO IMPROVE RELIABILITY, FUNCTION OR DESIGN OR OTHERWISE.

UN SEMICONDUCTOR LIMITED its affiliates, agents, and employees, and all persons acting on its or their behalf (collectively, "UNSEMI") does not give any representations or warranties for any errors, inaccuracies or incompleteness contained in any datasheet or in any other disclosure relating to any product.

In no event shall UNSEMI be liable for any indirect, incidental, punitive, special or consequential damages (including any and all implied warranties, warranties of fitness for particular purpose, non-infringement and merchantability.) whether or not such damages are based on tort (including negligence), warranty, breach of contract or any other legal theory.

Statements regarding the suitability of products for certain types of applications are based on UNSEMI knowledge of typical requirements that are often placed on UNSEMI products in generic applications. Such statements are not binding, statements about the suitability of products for a particular application. It is the customer's responsibility to validate that a particular product with the properties described in the product specification is suitable for use in a particular application. Parameters provided in datasheets or specifications may vary in different applications and performance may vary over time. All operating parameters, including typical parameters, must be validated for each customer application by the customer's technical experts. Product specifications do not expand or otherwise modify UNSEMI's terms and conditions of purchase, including but not limited to the warranty expressed therein.

Unless otherwise agreed in writing, UNSEMI product is not designed, authorized or warranted to be suitable for use in medical life-saving, or life-sustaining application , nor in applications where failure or malfunction of a UNSEMI product can reasonably be expected to result in personal injury, death or severe property or environmental damage. UNSEMI and its suppliers accept no liability for inclusion or use of UNSEMI products in such equipment or applications and therefore such inclusion and/or use is at the customer's own risk.

All referenced brands, product names, service names and trademarks are the property of their respective owners.